



TECNOFOAM

Technical information

TECNOFOAM is Marvon's single-component polyurethane foam designed and developed to ensure fire resistance up to EI 180 of linear joint seals on wall and floor according to EN 1366-4.

TECNOFOAM contains a special prepolymer mixed with hydrocarbons used as propellants.

Application field

TECNOFOAM can be used on rigid wall (masonry, concrete or aerated concrete) and on rigid floor (concrete or aerated concrete).

It has a fire resistance up to EI 180 classified according to EN 13501-2 for:

- Linear joint and gap seals

Technical data

Fire resistance	Up to EI 180
Fire reaction	B-s1, d0
Characteristics	Single-component polyurethane foam
Weight	900 g/pcs
Thermal conductivity	0.029 W/mK
Expansion ratio	1:25/35
Increase of volume	Ca 20-30 dm ³ (l)
Installation temperature	5°C - 35°C
Temperature range	-40 - +90°C
Colour	Light red
Storage	12 months (in normal conditions)

Dimensions



COD.	ml
MA0TF505013	740

Packaging

- 740 ml cartridges in cardboard boxes with 12 items

Standard rules

- Test Standard: EN 1366-4
- Fire Classification Standard: EN 13501-2

Certifications

Classification Reports:

- I.G. 294977/3412FR - floor - linear joint D
- I.G. 332786/3781FR - wall - linear joint F

Technical specification

Supply and installation of single-component polyurethane foam TECNOFOAM, certified in accordance to EN 1366-4, for fire protection up to EI 180 of linear joint and gap seals on wall and floor.

The foam must be applied with the application nozzle through full wall depth.

For different applications please refer to Classification Reports I.G. 294977/3412FR and I.G. 332786/3781FR.

740 ml cartridges.

Marvon S.r.l. - Società a socio unico
Via Gargnà 6 - 25078 - Vestone (BS) ITALY
Telefono: +39 0365 81.390 - Fax: +39 0365 879.923
e-mail: marvon@marvon.com - www.marvon.com

Soggetta all'attività di direzione e coordinamento ex art. 2497 bis C.C.
da parte di Silmar Group S.p.A. - Codice Fiscale 02075160172

